

Spectrum processing :

No peaks omitted

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	29.11	51.39
Al K	14.91	15.61
Ti K	55.98	33.01
Totals	100.00	

Comment: 7



Spectrum processing :

No peaks omitted

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	32.34	54.80
Al K	15.71	15.78
Ti K	51.96	29.41
Totals	100.00	

Comment: 5



Spectrum processing :

No peaks omitted

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	33.15	55.74
Al K	15.43	15.39
Ti K	51.42	28.88
Totals	100.00	

Comment: 8



Spectrum processing :

Peak possibly omitted : 3.699 keV

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	30.26	53.05
Al K	13.46	14.00
Ti K	56.28	32.96
Totals	100.00	

Comment: 4



Spectrum processing :

No peaks omitted

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	22.72	44.15
Al K	11.34	13.07
Ti K	65.93	42.79
Totals	100.00	

Comment: 9



Spectrum processing :

Peak possibly omitted : 1.760 keV

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	26.08	48.44
Al K	11.89	13.09
Ti K	62.03	38.47
Totals	100.00	

Comment: 2



Spectrum processing :

No peaks omitted

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	33.96	56.74
Al K	14.79	14.65
Ti K	51.25	28.60
Totals	100.00	

Comment: 13



Spectrum processing :

No peaks omitted

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	29.73	52.44
Al K	13.51	14.13
Ti K	56.75	33.43
Totals	100.00	

Comment: 1



Spectrum processing :

No peaks omitted

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	22.17	43.38
Al K	11.39	13.21
Ti K	66.44	43.41
Totals	100.00	

Comment: 10



Spectrum processing :

Peak possibly omitted : 1.744 keV

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	33.17	55.69
Al K	15.71	15.64
Ti K	51.12	28.67
Totals	100.00	

Comment: 3



Spectrum processing :

Peak possibly omitted : 5.418 keV

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	35.42	57.93
Al K	16.01	15.53
Ti K	48.57	26.54
Totals	100.00	

Comment: 11



Spectrum processing :

Peak possibly omitted : 5.440 keV

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :



O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	24.04	45.88
Al K	11.52	13.03
Ti K	64.44	41.08
Totals	100.00	

Comment: 12



Spectrum processing :

Peak possibly omitted : 3.697 keV

Processing option : All elements analyzed (Normalised)

Number of iterations = 3

Standard :

O SiO₂ 1-Jun-1999 12:00 AM

Al Al₂O₃ 1-Jun-1999 12:00 AM

Ti Ti 1-Jun-1999 12:00 AM

Element	Weight%	Atomic%
O K	29.34	51.96
Al K	13.63	14.31
Ti K	57.03	33.73
Totals	100.00	

Comment: 6

