

Adherencia a la cizalla

Resultados para Product: Adherencia en brackets

Wednesday 23 March 2022

Individual Specimens

[CECOu051.TSQ]

Batch	Max Force N	Comp. Strength MPa	Strain at Max %	Breadth mm	Width mm
control poli - 1	68.5	14.89	3.773	1.420	3.240
control poli - 2	141.7	30.79	3.164	1.420	3.240
control poli - 3	100.0	21.74	2.710	1.420	3.240
control poli - 4	43.50	9.45	3.496	1.420	3.240
control poli - 5	78.5	17.06	3.842	1.420	3.240
control poli - 6	95.0	20.65	2.080	1.420	3.240
control poli - 7	38.33	8.33	1.904	1.420	3.240
n	7	7	7	7	7
Promedio	80.79	17.559	2.996	1.4200	3.240
Desv. Estandar	35.652	7.7491	0.7864	0	0