

Adherencia a la cizalla

Resultados para Product: Adherencia en brackets

Wednesday 16 March 2022

Individual Specimens

[CECOu051.TSQ]

Batch	Max Force N	Comp. Strength MPa	Strain at Max %	Breadth mm	Width mm
Policristalino - 1	121.5	26.41	25.33	1.420	3.240
Policristalino - 2	78.5	17.06	3.842	1.420	3.240
Policristalino - 3	71.5	15.54	13.67	1.420	3.240
Policristalino - 4	58.3	12.68	1.731	1.420	3.240
Policristalino - 5	135.0	29.34	1.599	1.420	3.240
Policristalino - 6	46.67	10.14	2.098	1.420	3.240
Policristalino - 7	118.5	25.76	4.221	1.420	3.240
n	7	7	7	7	7
Promedio	90.00	19.562	7.499	1.4200	3.240
Desv. Estandar	34.604	7.5213	8.920	0	0